TABLE OF CONTENTS

TABLE OF CONTENTS 2
1. SCOPE 3
1.1. TYPE 3
1.2. COMPOSITION 3
1.3. CLASS 3
2. REFERENCES 3
3. DEFINITIONS 4
4. PROCESS CONTROL DOCUMENT 5
4.1. MATERIAL REQUIREMENTS 5
4.2. APPROVED MACHINES 5
5. QUALIFICATION 5
6. FILAMENT FEEDSTOCK REQUIREMENTS 6
6.1. RETENTION OF QUALIFICATION STATUS 6
7. MATERIAL TEST METHODS 6
7.1. PRINTER EXTRUSION FORCE 7
7.2. MOISTURE 7
7.3. LINE DIAMETER & CROSS-SECTIONAL AREA 7
7.4. NITROGEN BURNOUT (Carbon Content) 7
7.5. AIR BURNOUT (Ash Content) 7
7.6. TENSILE STRENGTH 7
8. TEST FAILURE 7
9. SPOOL IDENTIFICATION 8
9.1. TRACEABILITY 8
10. STORAGE AND HANDLING OF FILAMENT (UN-VERIFIED) 8
11. SAFETY HAZARDOUS MATERIALS 8
12. ROUNDING OF VALUES 8
13. QUALITY MANAGEMENT SYSTEM 8
14. STATISTICAL PROCESS CONTROL 9
15. ACKNOWLEDGEMENT 9
16. REVISION HISTORY 9
APPENDIX A -

1. SCOPE

This specification establishes the requirements for the manufacturing of a Finished Goods Feedstock from receipt of Raw Feedstock Lot.

This specification does not cover the process of NCAMP Qualification, and is limited to establishing

ASTM D3878	Standard Terminology for Composite Materials
ASTM D4000	Standard Classification System for Specifying Plastic Materials
ASTM D7191	Standard Test Method for Determination of Moisture in Plastics by Relative Humidity Sensor
ASTM E29	Standard Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
CMH-17	Composite Materials Handbook (formerly MIL-HDBK-17)
DOT/FAA/AR-06/10	Guidelines and Recommended Criteria for the Development of a Material Specification for Carbon Fiber/Epoxy Fabric Prepregs
DOT/FAA/AR-07/3	Guidelines and Recommended Criteria for the Development of a Material Specification for Carbon Fiber/Epoxy Unidirectional Prepregs Update
ISO 9000	Quality Management Systems
NSP 100	NCAMP Standard Operating Procedures
NMS 755	NCAMP Materials Specification Onyx FR-A
NMS 754/1 Slash	NCAMP Materials Specification Slash Sheet
NTP AM-6754Q1	NCAMP Test Plan
NPS 86754	NCAMP Process Specification Markforged X7
MF WI-001	Printer Backpressure Testing

3. DEFINITIONS

The following definitions ap/F1 11.04 Tf1 0 0 1 230.45 394.39 Tm0 g0 G[(N)5(C)4(A)5(MP Proc)-4(e)9(ss)-4(Sp)13(e

6. FILAMENT FEEDSTOCK REQUIREMENTS

The testing defined in this section is the responsibilities of the Filament
repeated by the purchaser. Filament Lot Supplier will submit a test report/Certificate of Conformance (COC) Table 4 - Table 6.
The report will include the following information:

Filament Lot Supplier name and product designation
Test Inspection Records, including individual specimen values, to prove material conforms with this specification
Filament Lot number
Date of Manufacture
Raw Feedstock Lot number
A statement of conformity with this specification

Table 4 - Incoming Raw Feedstock Lot Property Requirements(1)

Properties	**Test Method(2)**	**Requirements**
Extrusion Force (7.1)	MF WI-001	kg
Moisture (7.2)	ASTM D7191	
Nitrogen Burnout Carbon Content (7.4)	ASTM D1603 / WI-0824	15.3 18.7%
Air Burnout Ash Content (7.5)	ASTM D5630 / WI-0816	2.5 3.1%
Tensile Strength (7.6)	ASTM D638 / WI-0812	

Table 5 - In-Process Filament Material Property Requirements(1)

Properties	**Test Method(2)**	**Requirements**
Cross-sectional Area (7.3)	PCD-000A Onyx FR-A	2.3000 2.5000 mm²
Single-axis Diameter (7.3)	PCD-000A Onyx FR-A	1.6925 1.8019 mm

Table 6 - Outgoing Filament Lot Property Requirements

Properties	**Test Method(1)**	**Requirements**
Moisture (7.2)	ASTM D7191	

6.1. RETENTION 0000912OF QU0912ALIFICAU0912ALIFICAU0912ALIFICi2ALI ST12A

7.1. PRINTER EXTRUSION FORCE

Filament Printer Extrusion Force must be tested according to MF WI-001 Printer Extrusion Force Testing. This test must examine the force developed by a Filament Spool when fed into a proprietary test fixture representing a Markforged print head. Note that this has no relation to extruder backpressure developed when manufacturing Filament Spools.

7.2. MOISTURE

Moisture testing must be performed on every Raw Material Lot prior to pre-impregnation in compliance to ASTM D7191. Moisture testing must again be performed on a representative sample of each Filament Lot prior to shipping in compliance to ASTM D7191.

7.3. LINE DIAMETER & CROSS-SECTIONAL AREA

Line diameter & cross-sectional area must be held to a specification defined in the PCD. Each must be evaluated at a minimum rate of 1 measurement per meter of material using an in-process noncontact measurement device.

Cross-sectional area must be calculated using at least two off-axis diameter measurements. All diameter measurements used in the calculation of cross-sectional area must be individually checked against the specification.

Filament Spools with missing diameter or cross-sectional area data must be segregated and handled

9. SPOOL IDENTIFICATION

Each Filament Spool must be labeled with a unique Spool ID and the corresponding Filament Lot ID. This labeling must additionally be affixed to the outside of the Filament Spool packaging.

9.1. TRACEABILITY

Filament Spools must be traceable to date of manufacture and Filament Lot. Filament Lots must be traceable to extruder and Raw Feedstock Lot.

10. STORAGE AND HANDLING OF FILAMENT

Sealed and unopened Filament Spools must have a minimum shelf life of 2 years from date of manufacture when stored in their original sealed packaging at temperatures between 55°F 90°F (13°C 33°C) and 0-90 %RH.

Once unsealed, Filament Spools must be stored in a Markforged Dry Box or another similarly sized air-tight container at temperatures between 55°F 90°F (13°C 33°C) and 0-90 %RH. Filament Spools must be stored in this manner for up to 1 year, but no more than 2 years total from manufacture date.

Filament Spools must spend no more than 15 minutes outside of either the original sealed packaging, a Markforged Dry Box, or a similarly sized air-tight container.

Filament Spools must always be stored with the desiccant pack(s) they are shipped with.

11. SAFETY HAZARDOUS MATERIALS

The materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials. As with any new industrial process, it is recommended that a hazard assessment is performed, taking into consideration the specifics of each location, personnel, and facility.

Equipment, materials, solutions, and emissions (if applicable) must be controlled, handled, used, and disposed of in accordance with all local, State, and Federal Government Safety, Health, and Environmental Affairs. It must be the sole responsibility of the user to ensure familiarity with, and practice, the safe and proper use of any materials and to take necessary precautionary measures to ensure the health and safety of personnel involved.

The Material Safety Data S0912 0 612 792 rD.G[T)-8(he)9(Ma)7(t)-4(y)11(m)ended th-4(yn92 re,7f1 0 0 1 468.7 32)

14. STATISTICAL PROCESS CONTROL

The supplier must establish and maintain procedures and requirements for an SPC system based on Key Process Variables (KPV). The KPV are the material properties required for batch release, and must be fully defined in the PCD.

The KPV monitoring must also be provided to material users, certification agencies, and NCAMP staff upon request, but proprietary information may be coded or normalized. Alternatively, the supplier may

15. ACKNOWLEDGEMENT

A vendor must mention this specification number and the applicable detail specification number and their revision letters, if any, in all quotations and when acknowledging purchase orders.

16. REVISION HISTORY

REV	DESCRIPTION	DATE	WHO
-	Initial release	4/21/2021	NCAMP
Rev A	1. Filament class, glass transition, melt temperature and composition requirements for outgoing filament testing were removed from section 6, section 7, and Appendix A. 2. Nitrogen burn out, air burn out and tensile strength of raw incoming feedstock requirements was included in section 6 and section 7.	8/9/2023	Neville Tay
Rev B	1. Table 2: Composition lead in was removed from the front of CF and FR. 2. 1.3. 3. 14 CFR 25.853 reference was removed from Section 2. 4. MMPDS reference was removed from Section 2. 5. MF WI-001-Printer Backpressure Testing was added as reference in Section 2. 6. MMPDS (formerly MIL-HDBK-5) reference removed from Section 3. 7. 8. wa -000A Onyx FR- 9. -		

APPENDIX A - KEY PROCESS VARIABLES

The following table outlines parameters and characteristics determined to be critical to the quality of a Filament